

CHARACTERISTIC	STANDARD	RESULT
Type of flooring	EN ISO 10582	Heterogeneous LVT
Installation method	-	Loose Lay
Total thickness	EN ISO 24346	5.0 mm
Wear layer thickness	EN ISO 24340	0.7 mm
Size wood (width and length)	EN ISO 24342	1219.2 x 228.6 mm
Size stone (width and length)	EN ISO 24342	457.2 x 457.2 mm
Acoustic backing	-	No
Surface treatment	-	Top Protection Plus
Embossing type wood	-	Regular (wood grain)
Embossing type stone	-	Regular (stone grain)
Side beveling	-	4-sided
Packing wood (psc / box)	-	8 pcs / box
Packing stone (psc / box)	-	8 pcs / box
Packing wood (sqm / box)	-	2.23 sqm / box
Packing stone (sqm / box)	-	1.67 sqm / box
Weight (g/m ²)	EN ISO 23997	9470 g/m ²
Dimension stability	EN ISO 23999	< 0.10 %
Squareness & straightness	EN ISO 24337:2006	< 0.20 mm
Flexibility	EN ISO 24344	< 10 mm no crack
Curling after exposure to heat	EN ISO 23999	0 mm
Residual indentation	EN ISO 24343-1	0.08 mm
Castor wheel chair	EN 425:2002	Suitable (25 000 revolutions) Type W
Slip resistance	DIN 51130	R10
	EN 13893 EN 14041: 2004/AC:2006	DS
Abrasion resistance	EN 15468:2016	Group T
Use classification	EN ISO 10874	33/42
Burning behaviour	EN 13501-1	Bfl-s1
	EN ISO 9239-1	
	EN ISO 11925-2	
Color fastness	EN ISO 105-B02	> 6
Chemical resistance	EN ISO 26987	Index 0, excellent
Electrical resistance	EN 1081	> 3.0 x 10 ¹⁰ Ω
Thermal resistance	EN 12667	0.018 m ² K/W
Underfloor heating	-	Max 27°C
Formaldehyde emissions	EN 14041:2004/AC:2006	E1
	EN 717-1	
Pentachlorophenol content	EN 14041:2004/AC:2006	Not detected DL PCP
TVOC after 28 days	ISO 16000	A+
REACH	Regulation (EU) No. 1907/2006	YES

