

CHARACTERISTIC	STANDARD	RESULT
Type of flooring	EN ISO 10582	Heterogeneous LVT
Installation method	-	Glue Down
Total thickness	EN ISO 24346	2.5 mm
Wear layer thickness	EN ISO 24340	0.55 mm
Size (width and length)	EN ISO 24342	130 mm (side length)
Acoustic backing	-	No
Surface treatment	-	Top Protection Plus
Embossing type	-	Regular (stone grain)
Side beveling	-	6-sided
Packing psc / box	-	64 pcs / box
Packing sqm / box	-	2.81 m ² / box
Weight (g/m ²)	EN ISO 23997	4400 g/m ²
Dimension stability	EN ISO 23999	≤ 0.05 %
Squareness & straightness	EN ISO 24342	≤ 0.08 mm
Flexibility	EN ISO 24344	< 10 mm no crack
Curling after exposure to heat	EN ISO 23999	≤ 1.0 mm
Residual indentation	EN ISO 24343-1	≤ 0.05 mm
Castor wheel chair	ISO 4918	suitable (25 000 revolutions) Type W
Slip resistance	DIN 51130	R10
	EN 13893 EN 14041: 2004/AC:2006	DS
Abrasion resistance	EN ISO 10582	Group T
Use classification	EN ISO 10874	23/33/42
Burning behaviour	EN 13501-1	Bfl-s1
	EN ISO 9239-1	
	EN ISO 11925-2	
Color fastness	EN ISO 105-B02	≥ 6
Chemical resistance	EN ISO 26987	Index 0
Electrostatic behaviour	EN 1815	0.1 kV
Thermal resistance	EN ISO 8302	0.019 m ² K/W
Underfloor heating	-	Max 27°C
Formaldehyde emissions	EN 14041:2004/AC:2006	E1
	EN 717-1	
Pentachlorophenol content	EN 14041:2004/AC:2006	not detected DL PCP
TVOC after 28 days	ISO 16000	A+
REACH	Regulation (EU) No. 1907/2006	PASS

